

# **woolscour**

## **WOOLSCOUR FOR GREASY WOOL**

**TO FILL THE MEASURE CHAMBER, UNSCREW THE CAP ON THE CHAMBER ONLY AND SQUEEZE THE BOTTLE, FORCING THE CONTENTS UP THE TUBE INTO THE MEASURE CHAMBER TO THE REQUIRED MARK.**

### **INSTRUCTIONS FOR SCOURING**

SCOUR BY HAND ONLY - DO NOT USE WASHING MACHINE - DO NOT AGITATE. PLACE 20ML WOOLSCOUR INTO EACH 10LT HOT WATER INTO TUB OR BUCKET.

SUBMERGE THE FLEECE OR SPUN YARN IN THE HOT WATER SOLUTION AND LEAVE FOR 5 MINUTES. THEN GENTLY PADDLE THE FLEECE DOWN TO RELEASE ANY DIRT AND GREASE.

WHEN IT APPEARS THAT NO MORE DIRT IS BEING RELEASED, THE TIED SKEINS OR FLEECE CAN BE SPUN IN A WASHING MACHINE IF SO DESIRED. IF WASHING BY HAND GENTLY SQUEEZE THE YARN / FLEECE - DO NOT WRING.

PLACE THE YARN / FLEECE BACK IN TO CLEAN HOT WATER AND RINSE GENTLY AND THOROUGHLY. REPEAT THE SCOURING PROCESS IF WATER BEADS A LOT OR YOU CAN STILL FEEL GREASE.

**NOTE:** WOOL CAN TOLERATE HOT WATER PRIOR TO KNITTING PROVIDED THE SCOUR AND RINSE TEMPERATURES ARE SIMILAR.

### **FOR ONGOING CARE OF WOOLLENS & NATURAL FIBRES USE WOOLSKIN SHEEPSKIN SHAMPOO & WOOLWASH**

MANUFACTURED BY  
TANTECH PTY LTD  
181 WILLIAMSON ROAD TAMBORINE QLD 4270  
AUSTRALIA  
PH: 61 7b 5543 6911  
FAX: 61 7 5543 6933  
WEB: [www.tantech.com.au](http://www.tantech.com.au)  
EMAIL: [tantech@bigpond.com](mailto:tantech@bigpond.com)